



Instytut Techniki Budowlanej (ITB)

Group of Testing Laboratories

accredited by the Polish Centre for Accreditation
Accreditation Certificate No. AB 023

TEST REPORT

LZP01-03072/24/Z00NZP-ENG

Client:	Fiberplast Biobased B.V. De Boeg 24 9206 BB DRACHTEN The Netherlands
Product name: (as specified by the Client)	RIWOOD FR CP series closed horizontal façade system end-use application
Date of issue:	10.03.2025

Fire Testing Laboratory (LZP)
fire@itb.pl

1. Information on the tests

Test start date: 28.01.2025

Test completion date: 28.01.2025

Test location:


In the laboratory LZP, in the following location: 2 Przemysłowa Str., 26-670 Pionki, Poland.

2. Product

2.1. Information provided by the Client

Product:

Painted RIWOOD FR profiles CP series closed façade system end-use application.




RIWOOD FR CP-SERIES - CLOSED FACADE SYSTEM END-USE APPLICATION
HORIZONTALLY MOUNTED SOLID PROFILES WITH SANDED WOODGRAIN STRUCTURE
UNPAINTED AND - OPTIONAL - PAINTED WITH COLOUR STAIN AND SEALER

ITEM NO.	COMPONENT	DESCRIPTION	Class
1	CP siding profile width >95mm thickness >12mm	installed in horizontal orientation	B-s3-d0
2	Flame Delay PT black wooden joist	installed in horizontal orientation 28 x 44mm c.t.c. 300mm	B-s2-d0
3	Flame Delay PT black wooden joist	installed in vertical orientation 19 x 44mm c.t.c. 600mm	B-s2-d0
4	Swisspearl Extreme	Windstopper 9mm, close corners and gaps with Swisspearl self-adhesive tape	A2-s1-d0
5	IKO insulation	Enertherm ALU Class 140mm alternative: insulation with Class A1	F
6	SLS wooden batten	38mm x 140mm c.t.c. 600mm alternative: spacer screws	D
7	OSB	Oriented Stranded Board 18mm	E1

REMARKS

- use special shoulder screws SS A4
- the horizontal wooden joist must have a 15 degree angle at the top sloping towards the air
- cavity between the RIWOOD profiles and the Windstopper
- a ventilated air gap of at least 20mm between the RIWOOD profiles and Windstopper
- installation of components according to the manufacturers installation manual

UNLESS OTHERWISE SPECIFIED: DIMENSIONS ARE IN MILLIMETERS SURFACE FINISH: TOLERANCES: UNLESS INDICATED: ANGLE: 90°	FINISH: STANDARD & INSPIRATION	DEBRISS AND BREAK SHARP EDGES	DO NOT SCALE DRAWING	REVISION
BlondCode	SorVyl GK 60960 NATUR-FR/NF-R 8/23			
Producer	 FIBERPLAST BIOBASED B.V.			
DRWN:	NAME:	SIGNATURE:	DATE:	
CHKD:				
APPVD:				
MFG:				
QA:				
	MATERIAL:	PROFILE TYPE		
	RIWOOD FR	CP-series siding profile		
	WEIGHT:	SCALE: 1:20	SHEET 1 OF 1	

Description of internal CP profiles painted:

Thickness: 12 mm

Width: 128 mm (covering: 95mm)

Paint consumption: 0,1 l/m²

Varnish wear: 0,1 l/m²

Surface mass: 10,85 kg/m²

Declared range of application: Closed façade system.

3. Test item, sample

3.1. Information provided by the Client

Sample origin:

The product sample was provided by the Client in accordance with the Laboratory's recommendations

3.2. Information obtained based on visual inspection in the Laboratory

Acceptance of the test item into the laboratory:

Date: 25.01.2025

Acceptance protocol: LZP-03072/24/Z00NZP

Condition of the test item:

The product sample was provided in a condition and quantity suitable for testing.

Description of the test item:

Thickness samples: 20 cm

Thickness CP facade profiles: 12 mm

Surface mass of CP facade profiles: 10,92 kg/m²

Storage of the test item:

Test specimens were conditioned from 25.01.2025 to 28.01.2025 at temperature 23 ± 2°C, relative humidity 50 ± 5% until a constant weight was reached.

4. Test results

4.1. Reaction to fire test

4.1.1. Test method

PN-EN 13823+A1:2022-12

The implementation of the test, environmental conditions, and the accuracy of the measuring devices used are in accordance with the requirements of the above-mentioned standards.

Substrate made of chipboard board in accordance with PN-EN 13238+A1:2014. CP profiles mechanically assembled in horizontal.

Table 1 Test conditions

Parameter / Unit	Specimen 1	Specimen 2	Specimen 3
Fume volume flow [m ³ /s]	0,583-0,617	0,583-0,619	0,578-0,630
Ambient temperature [°C]	19,83	20,93	20,19
Ambient pressure [kPa]	98,473	98,445	98,393
Relative humidity [%]	38,7	38,7	36,4

4.1.2. Results

Table 2 Test results

Parameter / Unit	Specimen 1	Specimen 2	Specimen 3	Average value
FIGRA _{0,2 MJ} [W/s]	58,1	68,1	75,4	67,2
FIGRA _{0,4 MJ} [W/s]	58,1	68,1	74,5	66,9
THR _{600 s} [MJ]	6,6	6,3	6,1	6,3
SMOGRA [m ² /s ²]	118,7	129,6	137,6	128,6
TSP _{600 s} [m ²]	1500,0	1552,4	1498,5	1517,0

Table 3 Observations

Recorded events	Specimen 1	Specimen 2	Specimen 3
Lateral flame spread on the long specimen wing up to the edge of the specimen LFS [m]	0,35	0,30	0,30
Flaming droplets/particles in the first 600 s of the test, which flame less than 10 s (+/-)	-	-	-
Flaming droplets/particles in the first 600 s of the test, which flame more than 10 s (+/-)	-	-	-
Surface flash (+/-)	+	+	+
Falling of specimens parts (+/-)	-	-	-

Smoke entering the hood (+/-)	-	-	-
Damage of the mutual fixing of backing boards (+/-)	-	-	-
Distortion/collapse of the specimen (+/-)	-	-	-
Early termination of the test (+/-)	-	-	-

5. Assessment of the conformity of test results with the criteria

In accordance with the provisions of the PN-EN 13501-1:2019-02 standard, the assessment of compliance of the results with the criteria is included in classification report no 03072.1/24/Z00NZP-ENG.

The parties agreed that when assessing the compliance of the results with the criteria in accordance with the PN-EN 13501-1:2019-02 standard, the simple acceptance rule is applied. This means that the acceptance limits are equal to the tolerance limits presented in the above-mentioned document.

Factors influencing the risk associated with the performance assessment carried out:

- the uncertainty of measurement as presented in Annex 1 for this test report,
- the uncertainty of the test method is not presented in the test standard,
- the level of representativeness of the sample tested by the laboratory in relation to the product population – knowledge of the variability of the product population and the representativeness of the sample provided to the laboratory is held by the manufacturer.

6. Disclaimers

The Testing Laboratory declares that the test results relate only to the sample received.

The test results relate to the behaviour of the test specimen of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The Test Report cannot be reproduced in any other form than as a whole without written permission of the Laboratory.

The Test Report does not replace documents required for placing construction products on the market or making them available.

This report has been issued in electronic form, with qualified electronic signatures of the persons responsible. A printout of this report is not an original document.

7. Annexes:

1. Photos of test specimen installation in the test apparatus, graphs of classification parameters, and calculation of extended uncertainties of test results.

Person responsible for tests

Łukasz Jarołowicz

e-signature

Person authorising the report

Bartłomiej K. Papis PhD. Eng.

e-signature

Head of the Laboratory LZP

Bartłomiej K. Papis PhD. Eng.

e-signature

A document bearing a qualified electronic signature whose certificate has already expired is still valid (the certificate was valid on the day the document was signed).

END OF THE REPORT






Photo 1 Total view of the exposed surface of the long wing




Photo 2 Close-up of the vertical outer edge of the long wing at a height of 500 mm above the floor of the trolley




Graph 1 Plot of HRR, THR, and FIGRA as a function of specimen no 1 test duration.




Graph 2 Plot of SPR, TSP, and SMOGRA as a function of specimen no 1 test duration.




Graph 3 Plot of HRR, THR, and FIGRA as a function of specimen no 2 test duration.



Graph 4 Plot of SPR, TSP, and SMOGRA as a function of specimen no 2 test duration.



Graph 5 Plot of HRR, THR, and FIGRA as a function of specimen no 3 test duration.



Graph 6 Plot of SPR, TSP, and SMOGRA as a function of specimen no 3 test duration.

			U	k		$\bar{X} - U$	$\bar{X} + U$
Próbka 1							
FIGRA _{0,2MJ}	58,1	±	3,1	2,0		55,0	61,3
FIGRA _{0,4MJ}	58,1	±	3,1	2,0		55,0	61,3
THR _{600s}	6,6	±	0,1	2,0		6,5	6,7
SMOGRA	118,7	±	2,7	2,0		116,0	121,4
TSP _{600s}	1500,0	±	11,9	2,0		1488,1	1511,9
Próbka 2							
FIGRA _{0,2MJ}	68,1	±	3,0	2,0		65,1	71,1
FIGRA _{0,4MJ}	68,1	±	3,0	2,0		65,1	71,1
THR _{600s}	6,3	±	0,1	2,0		6,2	6,4
SMOGRA	129,6	±	3,0	2,0		126,6	132,6
TSP _{600s}	1552,4	±	12,6	2,0		1539,8	1565,0
Próbka 3							
FIGRA _{0,2MJ}	74,5	±	2,8	2,0		71,7	77,3
FIGRA _{0,4MJ}	74,5	±	2,8	2,0		71,7	77,3
THR _{600s}	6,1	±	0,1	2,0		6,0	6,2
SMOGRA	137,6	±	3,3	2,0		134,3	140,9
TSP _{600s}	1498,5	±	12,5	2,0		1486,0	1511,0
Wartość średnia							
FIGRA _{0,2MJ}	66,9	±	3,0	2,0		63,9	69,9
FIGRA _{0,4MJ}	66,9	±	3,0	2,0		63,9	69,9
THR _{600s}	6,3	±	0,1	2,0		6,2	6,4
SMOGRA	128,6	±	3,0	2,0		125,6	131,6
TSP _{600s}	1517,0	±	12,4	2,0		1504,6	1529,3

Table. 4 Expanded uncertainties of test results (related to the accuracy of the devices used), determined according to EN/TR 16988

The determination of uncertainty takes into account both the variability due to the measurement and the variability due to the selection of samples.

The result with its uncertainty applies only to the tested samples. The uncertainty value cannot be assigned directly to the level of a given product's properties, because the laboratory does not know about the variability of its population, but only about the tested sample.